

Technical Data Sheet

Bondloc B2012 5 Minute Epoxy Resin

PRODUCT DESCRIPTION

B2012 is a flexible easy-to-use solvent free epoxy adhesive. Can be used to bond or repair almost any material; such as wood, metal, glass, ceramic, plastic and rubber. B2012 is a fast setting resin which hardens in 5 minutes with high bond strength, chemical resistance and is clear in appearance.

APPLICATIONS

B2012 is suitable for bonding a wide range of variety of surfaces including steel, aluminium, and galvanised iron. B2012 reacts within a few minutes to give a tough resilient bond on a wide variety of surfaces.

USEFUL HINTS/NOTES

- Clean & easy to use
- Viscous but not thixotropic
- Rapid curing

INSTRUCTIONS FOR USE

- Ensure that surfaces to be bonded are clean and free from grease, dirt, dust and any other contamination.
- Mix equal quantities either by weight or volume of the two parts and stir thoroughly until a colour is obtained.
 Where a static mixing nozzle is supplied the 2 parts will be mixed correctly upon dispensing.
- Apply to one surface and offer up the second surface. Clamp or jig together under light pressure.

Leave to cure at room temperature.

STORAGE

Stored under dry conditions in closed containers between 5 and 25°C B2012 will have a shelf life of 12 months.

TECHNICAL FEATURES

	Part 1	Part 2
Physical Form	Viscous liquid	Viscous liquid
Chemical Type	Ероху	Mercaptan and polyamide
Appearance	Clear	Clear
Mixed Viscosity 25°C	15,000 – 20,000 Pa.S	
Specific Gravity	1.1	
Mix Ratio	1:1vol/vol or wt/wt	
Work Life	As a mix: 5 mins	
Percent Solid	100	
Adhesive Set-up Time	2-3 hours.	

MECHANICAL PROPERTIES

Shore Hardness D	78-80 (ASTM D 2240)
Shear Strength (N/mm²)	14-18 (DIN 53283)
Peel Strength (N/mm²)	3-5 (ISO 4578)
Thermal Conductivity (W/mK)	0.1
Coefficient of thermal expansion (1/k)	60-120 x 10 E ⁻⁶
Dielectric Strength (kv/mm)	50-90
Volume Resistivity (OHM/cm)	3-5 x 10 E ¹²
Service Temperature	-40°C to +121°C (-40°F to 250°F)

CURED PERFORMANCE

Lap Shear Strength			
Substrate	Shear Strength/Failure Mode		
CRS/CRS	2,350 psi – Cohesive Failure		
Aluminium/Aluminium	1,950 psi – Cohesive Failure		
Copper/Copper	1,850 psi – Cohesive Failure		
FRP/FRP	900 psi – Cohesive Failure		
ABS/ABS	850 psi – Cohesive Failure		
Chemical Resistance			
Media	Lap Shear (ASTM D 1002) Strength in PSI		
Gasoline	2550		
Acetic acid (10%)	2180		
Xylene	2165		

HEALTH & SAFETY

Lubricating oil-HD30

Paraffin

Water @ 23°C

Water @ 90°C

This technical information sheet does not constitute a Safety Data Sheet (SDS). Before using this product ensure you have read and fully understood this products SDS

2400

2275

2355

2325

PACKAGING FORMAT

Cartridge......28ml, 50ml, 200ml, 400ml Clam.....28ml

Bondloc UK Ltd. Units 1 & 2 Bewdley Business Park Bewdley, Worcestershire DY12 2TZ, UK

+44 (0) 1299 269 269 sales@bondloc.co.uk

PRECAUTIONS: This product and the auxiliary materials normally combined with it are capable of producing adverse health effects ranging from minor skin irritation to serious systemic effects. None of these materials should be used, stored, or transported until the handling precautions and recommendations as stated in the Safety Data Sheets (SDS) for this and all other products being used are understood by all persons who will work with the product. Warranty: All products purchased from or supplied by Bondioc are subject to terms and conditions set out in the contract. Bondioc warrants only that its product will meet those specifications designated as such herein or in other publications. All other information supplied by Bondioc is consider accurate but are furnished upon the express condition the customer shall make its own assessment to determine the product's suitability for a particular purpose. Bondioc makes no other warranty, either express or implied, including those regarding such other information, the data upon which the same is based, or the results to be obtained from the use thereof; that any product shall be merchantable or fit for any particular purpose; or that the use of such other information or product will not infringe any patent.

