



# Technical Data Sheet

## Bondloc B390 2 Part Instant Adhesive

### PRODUCT DESCRIPTION

Bondloc B390 is a gap filling instant adhesive/ repair product with excellent adhesion to a very broad range of materials and surfaces. Curing times of only 4 minutes while a hard and tough polymer results within 8 minutes, working times (in-mixer) up to 10 minutes, total volumetric gap filling, with minimal volumetric shrinkage make this product an ideal repair adhesive filler. instant adhesion to most plastics, wood and metals including aluminum, and to porous and irregular surfaces. The gel consistency enables application in any orientation whilst the static mixing nozzle ensures uniform and precise application for exceptional user convenience.

Appearance (uncured comp. A)	Transparent gel
Appearance (uncured comp. B)	Cream opaque gel
Chemical Type	Ethyl Cyanoacrylate
Components	Two-part – requires mixing
Cure	By mixing
Technology	Cyanoacrylate
Viscosity	High, thixotropic gel

### TYPICAL CURING PERFORMANCE

Under normal conditions, the atmospheric moisture initiates the curing process. Although full functional strength is developed in a relatively short time, curing continues for at least 24 hours before full chemical resistance is developed.

### FIXTURE TIMES

Fixture time is the time at which an adhesive bond (250 mm<sup>2</sup>) is capable of supporting a 3kg load for 10 seconds. The fixture time will depend on the substrate. The table shows the

fixture time for different substrates using lap shears. depend on the substrate. The table below shows the fixture time for different substrates using lap shears.

	Time (s)	Strength (N/mm <sup>2</sup> )
ABS	30 – 60	9-12*
Aluminum A5754	5 – 20	3-7
Beech Wood	15 –30	14-15*
Mild steel	15 – 45	17-20
Pine Wood	45 – 75	11-13*
Polycarbonate	15 – 45	10-12*

\*Substrate Failure

### TYPICAL PROPERTIES OF UNCURED MATERIAL

#### PART A:

Specific gravity, 25 °C, g/cm<sup>3</sup>: 1.09  
 Viscosity, Brookfield, 25 °C, mPa·s (cP):  
 Spindle 14, speed 1.5 rpm 100.000 to 195000

#### PART B:

Specific gravity, 25 °C, g/cm<sup>3</sup>: 1.17  
 Viscosity, Brookfield, 25 °C, mPa·s (cP):  
 Spindle 14, speed 1.5 rpm 80.000 to 110.000

### MIXED

A and B: Open time at 25 °C: 4 – 8 minutes  
 Working time at 25 °C: 5 – 10 minutes  
 Glass Transition Temperature (T<sub>g</sub>, °C): 87.2  
 Shore D Hardness: 56

### GENERAL INFORMATION

Directions for use:

- 1) Before applying the glue, make sure the gluing surface is clean, dry and free of grease.
- 2) To assemble the syringe, first introduce the plunger, then exchange the cap with a mixer. Discard the first few drops.

Bondloc UK Ltd.  
 Units 1 & 2  
 Bewdley Business Park  
 Bewdley, Worcestershire  
 DY12 2TZ, UK

+44 (0) 1299 269 269  
 sales@bondloc.co.uk





# Technical Data Sheet

## Bondloc B390 2 Part Instant Adhesive

- 3) Apply the material on one of the two surfaces and assemble the two parts within 1 minute.
- 4) After uniting the substrates, 15-30 seconds are available for repositioning on the substrates. Press the two parts together firmly for around 30 seconds. After releasing the pressure, wait 5 minutes before good handling strength, 10 minutes for a fully cured material and 24 hours for full strength.
- 5) Make use of the syringe or discard the product at least every 2 minutes to avoid the product from polymerizing inside the mixer, if you do not want to replace the mixer.
- 6) After use, discard the mixer and replace the cap. Store the syringe in a cool and dry environment.
- 7) Optimal Storage: 2°C to 8°C. Storage below 2°C or greater than 8°C can adversely affect product properties.
- 8) Product shelf-life: 12 months.

### HEALTH & SAFETY

This technical information sheet does not constitute a Safety Data Sheet (SDS). Before using this product ensure you have read and fully understood this products SDS.

### PRODUCT DISCLAIMER

Bondloc offers this Technical Data Sheet ("TDS") for descriptive and informational use only. It is not a warranty, a contract or a substitute for expert or professional advice. Please also see the local product Safety Data Sheet for health and safety considerations. The statements, technical information, data, and recommendations contained in this TDS are provided 'AS IS' and are not warranted or guaranteed in any way. They represent typical results for the products and are based on Bondloc's research only. Since the conditions and methods of use of the products are beyond our control, Bondloc expressly disclaims any and all liability and damages of whatever kind or nature that may arise from any use of the products, the results therefrom, or reliance on the information contained herein. This TDS is one of several tools that may be used to help you find the product best suited for your needs. It is used at your own risk, and by using it, you are knowingly accepting and assuming any and all risks associated with its use and recommendations. BUYERS AND USERS ASSUME ALL RESPONSIBILITY AND LIABILITY FOR ANY AND ALL LOSS OR DAMAGE OF WHATEVER KIND OR NATURE ARISING FROM OR RELATED TO THE HANDLING OR USE OF BONDLOC'S PRODUCTS. The performance of the product, its shelf life, and application characteristics will depend on many variables, including but not limited to the kind of materials to which the product will be applied, the environment in which the product is stored and/or applied, and the equipment used for the application, among other things. Any change in any of these variables can affect the product's performance. You are responsible to test the suitability of any product in advance for any intended use or application. Bondloc does not guarantee the reliability, completeness, use, or function of the statements, technical information, data, and recommendations contained in this TDS.

Bondloc UK Ltd.  
Units 1 & 2  
Bewdley Business Park  
Bewdley, Worcestershire  
DY12 2TZ, UK

+44 (0) 1299 269 269  
sales@bondloc.co.uk

