



Composition: ·Inner tube: polyester elastomer.
·Reinforcement: one or two braids of "aramid" fiber.
·Cover: black pinpricked polyurethane.

Working temperature: From -40° C to +100° C limited to +70° C for air and water based fluids.

Part n°	DN	Ø in	Ø out	Working Pressure (bar)	Working pressure (psi)	Burst pressure (bar)	Burst pressure (psi)	Bending radius (mm)	Weight (kg/m)
MT28004	1/4"	6,5	11,5	350	5.000	1.400	20.000	50	0,170
MT28005	5/16"	8,1	13,4	300	4.300	1.200	17.200	55	0,210
MT28006	3/8"	9,7	15,5	280	4.000	1.120	16.000	60	0,270
MT28008	1/2"	13	19,9	245	3.500	980	14.000	80	0,400